

Murphy Laminated Veneer Lumber
Murphy Engineered Wood Division

PR-L292
Revised February 22, 2011

Products: Murphy T1 and T2 LVL Tension Lams
Murphy Engineered Wood Division, 412 West Central, Sutherlin, Oregon 97479
(541) 459-4545
www.murphyplywood.com

1. Basis of the product report:
 - 2009 and 2006 International Building Code (IBC): Section 104.11 Alternative Materials and 2303.1.9 Structural composite lumber
 - 2009 and 2006 International Residential Code (IRC): Section R104.11 Alternative Materials
 - ASTM D 3737-07 recognized by the 2009 IBC and IRC, and ASTM D 3737-03 recognized by the 2006 IBC and IRC
 - ASTM D 5456-05a recognized by the 2009 IBC and ASTM D 5456-03 recognized by the 2006 IBC
 - ANSI/AITC A190.1-07 recognized by the 2009 IBC and IRC, and ANSI/AITC A190.1-02 recognized by the 2006 IBC and IRC
 - AITC 402-2005, Standard for Structural Composite Lumber (SCL) for Use in Structural Glued Laminated Timber
 - APA Reports T2008P-10, T2008P-31, T2010P-60, and other qualification data
2. Product description:

Murphy T1 and T2 LVL Tension Lams are made with wood veneers laminated with grain parallel to the length of the member in accordance with the in-plant manufacturing standard approved by APA. Murphy T1 and T2 LVL Tension Lams are available in thicknesses from 1 to 1-3/4 inches, widths up to 24 inches and lengths up to 80 feet.
3. Design properties:

Table 1 lists the design properties and Table 2 lists the equivalent specific gravities for connection design for Murphy T1 and T2 LVL Tension Lams, which are intended primarily for use as the tension laminations of glulam layup combinations recognized by approved agencies defined in Section 1702.1 of the 2009 and 2006 IBC and Section R202 of the 2009 and 2006 IRC. Murphy T1 and T2 LVL Tension Lams meet the requirements of ANSI/AITC A190.1, AITC 402, and ASTM D 5456.
4. Limitations:
 - a) Murphy T1 and T2 LVL Tension Lams shall be designed, when appropriate, in accordance with the code using the design properties specified in this report.
 - b) Murphy T1 and T2 LVL Tension Lams shall be qualified and used in manufacturing glulam beams in accordance with the applicable provisions specified in ANSI/AITC A190.1.
 - c) Murphy T1 and T2 LVL Tension Lams are limited to dry service conditions where the average moisture content of lumber is less than 16 percent.
 - d) Murphy T1 and T2 LVL Tension Lams are produced at Murphy Engineered Wood Division, Sutherlin, Oregon, under a quality assurance program audited by APA.
 - e) This report is subject to re-examination in one year.

5. Identification:

The Murphy T1 and T2 LVL Tension Lams described in this report are identified by a label bearing the manufacturer's name (Murphy Engineered Wood Division) and/or trademark, the APA assigned plant number (1089), the product grade, the APA logo, the report number PR-L292, and a means of identifying the date of manufacture.

Table 1. Design Properties (Allowable Stress Design) for Murphy T1 and T2 Tension Lams^(a,b)

Property		Design Stress (psi)	
		T1 LVL Tension Lam	T2 LVL Tension Lam
Bending (F_b) ^(c)	Joist ^(d)	3,100	3,100
	Plank	3,100	3,100
Tension parallel to grain (F_t) ^(e)		2,570	3,050
Longitudinal shear (F_v)	Joist	290	290
	Plank	150	150
Compression parallel ($F_{c }$)		3,200	3,200
Compression perpendicular ($F_{c\perp}$)	Joist	750	750
	Plank	650	650
Modulus of Elasticity, E	Joist	2.00×10^6	2.00×10^6
	Plank	2.40×10^6	2.40×10^6

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa.

- (a) The tabulated values are design values for normal duration of load. All values, except for E and $F_{c\perp}$, are permitted to be adjusted for other load durations as permitted by the code. The design stresses are limited to conditions in which the maximum moisture content of lumber is less than 16 percent.
- (b) Joist = load parallel to glue-line. Plank = load perpendicular to glue-line.
- (c) Tabulated flexural stress (F_b) may be increased by 4 percent when the member qualifies as a repetitive member as defined in the NDS.
- (d) The tabulated values are based on a reference depth of 12 inches. For other depths, when loaded edgewise, the allowable bending stress (F_b) shall be modified by $(12/d)^{0.18}$, as shown in the following table. For depths less than 2-1/2 inches, the factor for the 2-1/2-inch depth shall be used.

Depth (in.)	2-1/2	3-1/2	5-1/2	7-1/4	9-1/4	11-1/4	12	16	18	20	24
Multiply by	1.33	1.25	1.15	1.09	1.05	1.01	1.0	0.95	0.93	0.91	0.88

- (e) The tabulated values are based on a reference length of 3 feet. For other lengths, the allowable tensile stress shall be modified by $(3/\ell)^{0.11}$, where ℓ = length in feet. For lengths less than 3 feet, use the allowable tension stresses in Table 1 unadjusted.

Table 2. Fastener Design for Murphy T1 and T2 Tension Lams^(a,b)

Equivalent Specific Gravity (S.G.)				
Nails				Bolts
Withdrawal Load		Lateral Load		Lateral Load
Installed in Edge	Installed in Face	Installed in Edge	Installed in Face	Installed in Face
0.50	0.50	0.50	0.50	0.50

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa.

- (a) Fastener values based on the equivalent specific gravities in the above table are for normal load duration and shall be permitted to be adjusted using the load duration factors in accordance with the code.
- (b) The bolt edge distance when loaded parallel and perpendicular to the grain shall be a minimum of four times the bolt diameter.

APA – The Engineered Wood Association is an accredited certification body under ISO 65 by Standards Council of Canada (SCC) and an accredited inspection agency by the International Code Council (ICC) International Accreditation Service (IAS) under ISO/IEC 17020. APA is also an accredited testing organization recognized by IAS and SCC under ISO/IEC 17025. APA is a recognized testing laboratory by Miami-Dade County, and a Product Testing Laboratory, Product Quality Assurance Entity, and Product Validation Entity by the Florida Department of Community Affairs (DCA).

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466
Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility of product performance or designs as actually constructed.